


2912



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) **EP 1 291 394 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
12.03.2003 Bulletin 2003/11

(51) Int Cl.7: **C09D 5/26**

(21) Application number: **02255947.0**

(22) Date of filing: **27.08.2002**

(84) Designated Contracting States:  
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR  
IE IT LI LU MC NL PT SE SK TR**  
Designated Extension States:  
**AL LT LV MK RO SI**

(72) Inventors:  
• **Watson, Hugh Michael Lawrence  
Derby DE22 3LS (GB)**  
• **Hodgkinson, Elaine Christine  
Oakwood, Derby DE21 2JW (GB)**

(30) Priority: **05.09.2001 GB 0121427**

(74) Representative: **Gunn, Michael Alan  
Rolls-Royce plc  
P.O. Box 31  
Derby DE24 8BJ (GB)**

(71) Applicant: **ROLLS-ROYCE plc  
London, SW1E 6AT (GB)**

(54) **A temperature indicating paint**

(57) An irreversible temperature indicating paint comprises 29wt% to 37wt% cobalt zinc silicon blue phenacite and a frit, 35wt% to 45wt% acrylic resin and 20wt% to 30wt% silicone resin excluding solvent. The solvent comprises a mixture of 80% 1-methoxy-2-propanol and 20% dipropylene glycol monomethyl ether. A particular irreversible temperature indicating paint comprises 34.9wt% cobalt zinc silicon blue phenacite and a

frit, 42.5wt% acrylic resin and 22.6wt% silicone resin excluding solvent. The irreversible temperature indicating paint is used to determine the temperatures to which various parts of turbine blades, turbine vanes or other components are subjected in operation of a gas turbine engine.

## Description

[0001] The present invention relates to an irreversible temperature indicating paint.

[0002] Irreversible temperature indicating paint changes colour at one or more known temperatures. These colour changes of the temperature indicating paint indicate the temperature to which different parts of a component or components have been subjected. The final colour of the irreversible temperature indicating paint is dependent on both the temperature it is subjected to and the time period over which it is held at a raised temperature. The irreversible temperature indicating paint is applied to a component in a test situation and subsequently analysed to determine the temperatures to which different regions of the component reached during the test. Irreversible temperature indicating paints thus produce a temperature profile over the whole surface of a component rather than discrete points, if for example thermocouples are used.

[0003] Irreversible temperature indicating paints are applied to components, for example turbine blades, turbine vanes and combustors, of gas turbine engines and the gas turbine engine is run at the gas turbine engines normal operating conditions.

[0004] One known temperature indicating paint described in our UK patent GB1103059 comprises principally lead chromate, magnesium carbonate and silica.

[0005] Another known temperature indicating paint described in our UK patent GB2204874 comprises one or more of silver, gold, platinum, palladium, copper, nickel, chromium, titanium and silicon dispersed in 10 to 70wt% solvent and resin.

[0006] Currently used temperature indicating paint used in the temperature range 500°C to 900°C does not provide sufficient resolution of the temperature.

[0007] Accordingly the present invention seeks to provide a novel irreversible temperature indicating paint which has a plurality of colour changes in the temperature range 500°C to 900°C to provide improved temperature resolution.

[0008] Accordingly the present invention provides an irreversible temperature indicating paint comprising cobalt zinc silicon blue phenacite, a frit, a binder and a solvent.

[0009] Preferably the binder comprises acrylic resin and silicone resin.

[0010] Preferably the irreversible temperature indicating paint comprises 29wt% to 37wt% cobalt zinc silicon blue phenacite and a frit, 35wt% to 45wt% acrylic resin and 20wt% to 30wt% silicone resin excluding solvent.

[0011] Preferably the irreversible temperature indicating paint comprises 33wt% to 37wt% cobalt zinc silicon blue phenacite and a frit, 37.5wt% to 45wt% acrylic resin and 21wt% to 27.5wt% silicone resin excluding solvent.

[0012] Preferably the irreversible temperature indicating paint comprises 34wt% to 36wt% cobalt zinc silicon blue phenacite and a frit, 40wt% to 45wt% acrylic resin

and 22wt% to 25wt% silicone resin excluding solvent.

[0013] Preferably the irreversible temperature indicating paint comprises 34.9wt% cobalt zinc silicon blue phenacite and a frit, 42.5wt% acrylic resin and 22.6wt% silicone resin excluding solvent.

[0014] Preferably the solvent comprises a mixture of propylene glycol ethers. Preferably the solvent comprises a mixture of 80% 1-methoxy-2-propanol and 20% dipropylene glycol monomethyl ether.

[0015] The present invention will be more fully described by way of example.

[0016] An irreversible temperature indicating paint according to the present invention has four or more colour changes in the temperature range 500°C to 900°C when run at maximum operating conditions of a gas turbine engine, or other engine, for 3 minutes.

[0017] The irreversible temperature indicating paint comprises cobalt zinc silicon blue phenacite, a frit, a binder and a solvent.

[0018] The irreversible temperature indicating paint broadly comprises 29wt% to 37wt% cobalt zinc silicon blue phenacite and a frit, 35wt% to 45wt% acrylic resin and 20wt% to 30wt% silicone resin excluding solvent. The solvent comprises a mixture of propylene glycol ethers, for example the solvent comprises a mixture of 80% 1-methoxy-2-propanol and 20% dipropylene glycol monomethyl ether. The amount of solvent used is varied depending upon the particular method of applying the irreversible temperature indicating paint.

[0019] The irreversible temperature indicating paint more narrowly comprises 33wt% to 37wt% cobalt zinc silicon blue phenacite and a frit, 37.5wt% to 45wt% acrylic resin and 21wt% to 27.5wt% silicone resin excluding solvent.

[0020] Preferably the irreversible temperature indicating paint comprises 34wt% to 36wt% cobalt zinc silicon blue phenacite and a frit, 40wt% to 45wt% acrylic resin and 22wt% to 25wt% silicone resin excluding solvent.

[0021] A particular irreversible temperature indicating paint comprises 34.9wt% cobalt zinc silicon blue phenacite ( $\text{Be}_2\text{SiO}_4$ ) and a frit, 42.5wt% acrylic resin and 22.6wt% silicone resin excluding solvent. The cobalt zinc silicon blue phenacite and frit is sold under the trade name 121601 Decorating Colour Lazulite Blue by Degussa Metals Catalysts Cerdec AG of Geschäftsbereich Cerdec, P.O. Box 110403, D-60039 Frankfurt, Germany. Phenacite is the common name for beryllium orthosilicate. Cobalt zinc silicon blue phenacite is a phenacite comprising cobalt, zinc and silicon which has a blue colour.

[0022] Decorating Colour Lazulite Blue 121601 comprises cobalt zinc silicon blue phenacite having a CAS-No 68412-74-8 and a frit having a CAS-No 65997-18-4.

[0023] The irreversible temperature indicating paint has four or more colour change points in the temperature range 500°C to 900°C. The irreversible temperature indicating paint has improved temperature resolution.

tion in the temperature range 500°C to 900°C, particularly in the temperature range 600°C to 800°C.

[0024] The irreversible temperature indicating paint is applied to turbine blades or turbine vanes or other components of gas turbine engines. The irreversible temperature indicating paint is used to determine the temperatures to which various parts of the turbine blade, turbine vane or other component are subjected in operation of the gas turbine engine.

[0025] The irreversible temperature indicating paint may be used on components in other engines or other machines or other apparatus to determine the temperature to which various parts of the component are subjected in operation.

### Claims

1. An irreversible temperature indicating paint comprising a binder and a solvent, **characterised in that** the irreversible temperature indicating comprising cobalt zinc silicon blue phenacite and a frit.
2. An irreversible temperature indicating paint as claimed in claim 1 wherein the binder comprises acrylic resin and silicone resin.
3. An irreversible temperature indicating paint as claimed in claim 1 or claim 2 comprising 29wt% to 37wt% cobalt zinc silicon blue phenacite and a frit, 35wt% to 45wt% acrylic resin and 20wt% to 30wt% silicone resin excluding solvent.
4. An irreversible temperature indicating paint as claimed in claim 3 comprising 33wt% to 37wt% cobalt zinc silicon blue phenacite and a frit, 37.5wt% to 45wt% acrylic resin and 21wt% to 27.5wt% silicone resin excluding solvent.
5. An irreversible temperature indicating paint as claimed in claim 4 comprising 34wt% to 36wt% cobalt zinc silicon blue phenacite and a frit, 40wt% to 45wt% acrylic resin and 22wt% to 25wt% silicone resin excluding solvent.
6. An irreversible temperature indicating paint as claimed in claim 5 comprising 34.9wt% cobalt zinc silicon blue phenacite and a frit, 42.5wt% acrylic resin and 22.6wt% silicone resin excluding solvent.
7. An irreversible temperature indicating paint as claimed in any of claims 1 to 6 wherein the solvent comprises a mixture of propylene glycol ethers.
8. An irreversible temperature indicating paint as claimed in claim 7 wherein the solvent comprises a mixture of 80% 1-methoxy-2-propanol and 20% dipropylene glycol monomethyl ether.

EP 1 291 394 A1



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 02 25 5947

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A.D	GB 1 103 059 A (ROLLS ROYCE) 14 February 1968 (1968-02-14)		C09D5/26
A.D	GB 2 204 874 A (ROLLS ROYCE PLC) 23 November 1988 (1988-11-23)		
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C09D G01K
The present search report has been drawn up for 34 claims			
Place of search <b>THE HAGUE</b>		Date of completion of the search <b>6 December 2002</b>	Examiner <b>Miller, A</b>
<p><b>CATEGORY OF CITED DOCUMENTS</b></p> <p>X : particularly relevant if taken alone  Y : particularly relevant if combined with another document of the same category  A : technological background  O : non-written disclosure  I : intermediate document</p> <p>1 : theory or principle underlying the invention  2 : earlier patent document, but published only after the filing date  3 : document cited in the application  4 : document cited for other reasons  5 : member of the same patent family, corresponding document</p>			